



Bedford Materials Co., Inc.
 7676 Allegheny Rd
 Manns Choice, PA 15550
 Phone: (814) 623-9014
 Fax: (814) 623-9199
 E-Mail: bedmat@bedford.net

Pyromid 180

Pyromid 180 Mat/Film/Mat

Product	Nominal Thickness (inches)	Weight (Lbs./Sq.Yd.)	Yield (Sq.Yds./Lb.)	Dielectric Breakdown ASTM D149 2" Electrode (Volts)	Tensile ASTM D828 lbs./In.		Graves Tear ASTM D1004 lbs.		Elemdorf Tear ASTM D1922 GMS	
					MD	CMD	MD	CMD	MD	CMD
2-3-2	0.0085	0.35	2.86	10,000	91	103	6	4	166	266
2-5-2	0.0105	0.48	2.08	14,000	124	166	10	7	261	346
2-7½-2	0.013	0.65	1.54	20,000	175	191	14	13	387	536
2-10-2	0.0152	0.80	1.25	21,000	232	251	19	16	557	898
2-14-2	0.019	1.04	0.96	27,000	274	319	28	28

Product	Nominal Thickness (inches)	Weight (Lbs./Sq.Yd.)	Yield (Sq.Yds./Lb.)	Dielectric Breakdown ASTM D149 2" Electrode (Volts)	Tensile ASTM D828 lbs./In.		Graves Tear ASTM D1004 lbs.		Elemdorf Tear ASTM D1922 GMS	
					MD	CMD	MD	CMD	MD	CMD
3-3-3	0.010	0.46	2.17	10,000	136	113	10	7	379	930
3-5-3	0.012	0.59	1.69	13,000	164	177	13	10	592	1290
3-7½-3	0.015	0.78	1.28	18,000	213	232	20	15	1006	1520
3-10-3	0.017	0.92	1.09	23,000	265	326	24	21
3-14-3	0.0215	1.19	0.84	27,000	343	364	37	32	1056	2137